










		Standard	Result
	Size	ISO 24342	1500 x 250 mm
	Thickness	ISO 24346	4.5 mm
	Wear Layer		0.5 mm
	Surface treatment		K-Guard+ PU coating
	Backing		PVC Friction Pad
	K-Guard+		Yes
	Box quantity		8 Planks / 3.00 m ²
	Warranty	Commercial Residential	15 years wear* Lifetime wear*
	Bevelled Edge		No
  	Standards	ASTM F1700	Pass
	Classification		Commercial Heavy Duty use Domestic Extra Heavy Duty use
	Staining Resistance	EN 423 ASTM F925	Class 0 Pass
	Colour Fastness to Light	ISO 105-B02 ASTM F1515	≥7 <8
 	Abrasion Resistance	EN 660-2 ISO 10582 ASTM D3884	Group T Type 1 Pass
	Flexibility	ISO 24344	Pass
	Dimensional stability	EN 434/ISO 23999 ASTM F2199	≤ 0.10% Pass
  	Acoustic Impact noise reduction	NCC 2016 F5.3 (a) result refer to Karndean INSUL Marshall Day Software report for your MULTI Res specification including AAC Star rating ISO 140-8 Improved Impact Sound Insulation ASTM E492-09 Impact Insulation Class	 $\Delta L_w = 14\text{dB}$ IIC 56dB
	Electrical behaviour body voltage	EN 1815 AATCC 134-1996	Pass Pass
	Indentation - residual	EN 433/ ISO 24343-1 ASTM F1914	≤ 0.1mm <8%
	Castor chair continuous use	EN 425/ ISO 4918	Pass
  	Thermal resistance	ISO 8302	0.0245 m ² K/W Suitable for underfloor heating
	Reaction to Fire	AS/NZS ISO 9239.1:2003	CRF: 8.3 kW/m ² Smoke value: 143% min
	**Slip resistance	AS/NZS 4586:2013	R10
	Adhesive		Karndean Hi-Tack PS Adhesive when applicable. Please refer to Installation Guidelines.
	Recycling		Suitable
	Environmental	Floorscore (SCS-EC10.2-2007)	Indoor air quality certified; Compliant low emitting VOC emissions.
	Phthalate free		Yes

*Subject to terms

**Slip resistance is measured on ex-factory product. Slip resistance in use will be affected by surface contamination and by how the product is maintained

For more information:

Australia
Call: 1800 33 11 70
Email: customerservice@karndean.com.au
Visit: www.karndean.com

New Zealand
Call: 0800 44 21 01
Email: customerservice@karndean.co.nz
Visit: www.karndean.com